

Material Data Sheet

Fluoroloy® A15

Features/Benefits:

- Color: Dark Gray
- Soft material
- Good for sealing at low pressures
- Can be abrasive running against soft metals
- Good heat resistance
- Working Temperature Range: -268° to +316°C [-450° to +600°F]

The table below represents typical values

Properties ¹	ASTM	Value	Units
PHYSICAL			
Specific Gravity	D792	2.23	-
MECHANICAL			
Tensile Strength	D4894	23.4 [3,400]	MPa [psi]
Tensile Modulus	D4894	441 [64,000]	MPa [psi]
Elongation	D4894	230	%
Compression Strength ²	D695	13.1 [1,900]	MPa [psi]
Compressive Modulus	D695	827 [120,000]	MPa [psi]
Deformation Under Load ³	D621	8.5	%
Hardness	D2240	58	Shore D
Coefficient of Friction	D3702	0.09	-
THERMAL			
Linear Coefficient of Thermal Expansion 26° to 200°C [78° to 392°F] Mold Direction Cross Direction	E831	12.9x10 ⁻⁵ [7.17x10 ⁻⁵] 9.35x10 ⁻⁵ [5.19x10 ⁻⁵]	mm/mm/°C [in/in/°F] mm/mm/°C [in/in/°F]

1. All testing is performed at room temperature unless otherwise specified.
2. Compression Strength was measured at 1% Strain.
3. Deformation Under Load was tested at 13.8 MPa [2,000 psi] for 24 hours

NOTE: The data listed falls within the normal range of properties but should not be used to establish specification limits nor used solely as the basis of design. Saint-Gobain Performance Plastics assumes no obligation or liability for any advice furnished by the Company or for results obtained with respect to the products.

Saint-Gobain Performance Plastics – Seals

OmniFlex™ and RACO™ are trademarks. DynaLip®, Fluoroloy®, Elgiloy®, Meldin®, Marathon®, OmniSeal® and Rulon® are registered trademarks.
©2009 Saint-Gobain Performance Plastics Corporation

USA: Garden Grove, CA
Toll Free: (800) 544-0080
Fax: (714) 688-2701

Europe: (32) 34 58 28 28
South America: (55) 19 2127 8530

Japan: (81) 266 79 6400
China: (86) 21 54 72 1568

Email: seals.marketing@saint-gobain.com
Website: www.seals.saint-gobain.com
www.rulon-meldin.com